



45° ADAPTER

Material Description	Dimensions						Material Thickness
	A	B	C	D	E	F	
AAP-35-45AD 45° Adapter	3"	5"	4"	10"	4.5"	3.5"	1/8"
AAP-39-45AD 45° Adapter	3"	9"	5"	10"	3.5"	4"	3/16"
AAP-312-45AD 45° Adapter	3"	12"	6"	15"	5.5"	4"	3/16"
AAP-317-45AD 45° Adapter	3"	17"	8"	15"	4"	3.5"	3/16"
AAP-327-45AD 45° Adapter	3"	27"	10"	-	-	-	3/16"
AAP-414-45AD 45° Adapter	4"	14"	8"	15"	4"	3"	3/16"
AAP-420-45AD 45° Adapter	4"	20"	10"	-	-	-	3/16"

ENGINEERING DATA Advanced Aquaduck cold-formed, welded, hollow rectangular steel pipe and fittings are produced in accordance with mechanical and chemical property requirements of ASTM specification A500 grade "B". Tensile Strength minimum: 58,000 psi. Yield Point minimum: 46,000 psi.

COATING Asphalt emulsified with bentonite clay. Complies with ASTM D-1227-87 Type III and ASTM D-1187-82 Type I.

COATING APPLICATION Immersion

METHOD CONNECTION Rectangle to rectangle connections; lead and oakum, lead wool, epoxy bonding method, or other approved method. Cast iron or plastic pipe connection shall use cast iron or plastic to steel, no-hub style couplings.

Representative: